

# Compset UHS epoxy

## Compset protective coatings

### Description :

**Compset UHS** is a solventless, high build, heavy duty epoxy coating for the protection of concrete floors and walls against chemical attack and mechanical abrasion in industrial installations. The surface finish of **Compset UHS** makes this system ideal for applications where hygiene and cleanliness are important. **Compset UHS** is suitable for the coating of water treatment tanks and is recommended for use in the food processing, hospital, school, automotive and marine industries.

### Advantages:


- Solvent free
- High Build
- Excellent abrasion and scratch resistance
- Chemical resistant

### Usages:

- Food processing industry
- Education facilities
- Mining and Construction industries
- Warehousing

### Application data:

<b>VOC content:</b>	< 20 grams / litre
<b>Mixing Ratio by volume:</b>	3 Resin to 1 Hardener
<b>Working time:</b>	30 mins at 25°C Standard 30 mins at 15°C Fast grade
<b>Minimum substrate temp</b>	10°C
<b>Application rate:</b>	First coat 4 - 6m <sup>2</sup> /L Second coat 6 - 8m <sup>2</sup> /L
<b>Film thickness:</b>	350 - 400 µm
<b>Recoat time @25°C</b>	16 - 48 hours
<b>Light traffic:</b>	24 hours 25°C
<b>Cure time:</b>	7 days



### Engineering data:

<b>Shore D hardness:</b>	75
<b>Tg DSC °c ultimate</b>	54
<b>Compressive strength MPa</b>	35
<b>Tensile strength Mpa</b>	12
<b>elongation %</b>	4
<b>Taber Abrasion 1kg 1000 cycles</b>	
<b>C17 µm loss</b>	118
<b>H22 µm loss</b>	265
<b>Adhesion to concrete MPa</b>	> 1.70

### Typical chemical resistance : spillages

- Skydrol
- Gasolene
- Acetic Acid 5%
- Sodium Hydroxide 30%
- Vegetable oils
- Sulphuric Acid 20%
- Ammonia solution
- Jet fuel
- Organic detergents

### Application instructions :

Concrete surfaces should be clean and free of additives, curing agents and contaminants. Prepare by diamond grind, track or light shot blast to provide suitable profile.

Cement based substrates should be at least 21 days old before coating.

Test for rising damp or back water pressure before application as adhesion failure is likely to occur.

Old concrete floors previously contaminated with fats and oils should be tested for adhesion before application of epoxy compounds.